

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 121 COLOUR RETAINING PRIMER

(Page 1 of 3)

V1-28/11/2014

DESCRIPTION

- Dekster 121 is a water based penetrating primer, designed for easy and safe application, to retain the natural colour effects of stone and cement based surfaces. Usually over-coated with clear polyurethane or epoxy top coats.

PROPERTIES

- Penetrates most cement surfaces
- Easy to apply.
- No solvents, clean equipment with water.
- Good UV resistance.

RECOMMENDED AREAS FOR USE

- Counter tops
- Ablution blocks
- Schools and hospitals
- Kitchens
- Passages and walkways

SURFACE PREPARATION

- All surfaces to be clean and sound. Free of dust, oil and grease. New concrete should be acid etched to remove surface laitance.

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 121 COLOUR RETAINING PRIMER

(Page 2 of 3)

V1-28/11/2014

APPLICATION

- Apply by sponge, brush or roller to achieve the desired effect.
-

SEALING

- Depending on the final finish required a suitable sealer and wear resistant top- coat should be applied. (Contact a Dekster technical representative for specialist advice).
-

CLEANING EQUIPMENT

- Clean all equipment immediately after use with water.
-

TOXICITY

- Dekster 121 is a relatively non-toxic and safe to use water based stain. Refer to the relevant 16 point Material Safety Data Sheet.
-

HOW TO SPECIFY

- All surfaces to be suitably prepared and coated with Dekster 121 Colour Retaining Primer, applied according to the manufacturer's instructions.
-

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 121 COLOUR RETAINING PRIMER

(Page 3 of 3)

V1-28/11/2014

TECHNICAL DATA

TYPE	: Urethane Acrylic
NUMBER OF COMPONENTS	: 1
VOC	: 5
COLOURS	: See Colour Chart
FINISH	: Satin
NUMBER OF COATS	: 1 or 2
OVERCOATING TIME	: 2hrs – 4hrs
TOUCH DRY	: 2hrs (25 °C)
SOLIDS (By Volume)	: 40%
AVERAGE SPREAD RATE	: 8 - 10m ² /l/coat
APPLICATION TEMPERATURE	: 5 to 40°C
SHELF LIFE	: 12 Months
PACKAGING	: 1, 5 and 20 litres

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.