

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 401 POLYMER CEMENT ADDITIVE

(Page 1 of 3)

V1-28/11/2014

DESCRIPTION

- A Latex emulsion admixture used to waterproof and improve the properties of cement screeds, slurries and mortars.

PRACTICAL USES

- Water- resistant renderings.
- Damp-proof layers.
- A bonding liquid for plaster.
- A tile adhesive.
- Waterproofing of ponds, reservoirs, retaining walls and silos.

ADVANTAGES

- Increased adhesion.
- Allows thin application of slurries and screeds.
- Improved flexibility and impact resistance.
- Improved water resistance.
- Improved chemical and stain resistance.

PREPARATION

- Surface must be clean, sound and free from oil and contaminants. Remove all loose surface laitance by acid etching. Pre-dampen surface with clean water prior to application.

MIXING

- Ensure thorough mixing of all components using a slow speed mechanical mixer.

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 401 POLYMER CEMENT ADDITIVE

(Page 2 of 3)

V1-28/11/2014

TYPICAL QUANTITIES

	Bonding & Bagging Slurry		Waterproof Slurry		Light Duty Screed		Heavy Duty Screed	
	5L	5kg	5L	5kg	5L	5kg	5L	5kg
Dekster 401	5L	5kg	5L	5kg	5L	5kg	5L	5kg
Water	5L	5kg	5L	5kg	5L	5kg	5L	5kg
Portland Cement	10L	15kg	15L	18kg	40L	50kg	40L	50kg
Plaster Sand	10L	16kg	-	-	-	-	-	-
River Sand	-	-	-	-	100L	150kg	75L	100kg
Stone 6 – 9mm	-	-	-	-	-	-	50L	75kg
YIELD (VOLUME)	20L		15L		90L		100L	

- The waterproofing slurry may be reinforced with a polyester membrane when used as a lining or to bridge gaps.

HOW TO SPECIFY

- All surfaces to be prepared and waterproofed with Dekster 401 Polymer Cement Additive according to the manufacturer's instructions.

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 401 POLYMER CEMENT ADDITIVE

(Page 3 of 3)

V1-28/11/2014

TECHNICAL DATA

No. OF COMPONENTS	: 1
COLOUR	: Milky White
CONSISTENCY	: Liquid
DENSITY	: 1.00
POT LIFE (WITH CEMENT)	: 90 minutes
INITIAL CURE	: 24 hours
FULL CURE	: 28 days
COMPRESSIVE STRENGTH OF SCREED	: >25mPa
PACKAGING	: 5L & 25L
SHELF LIFE	: 12 months

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.