

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 411 WALL/FURNITURE WAX

(Page 1 of 4)

V1-28/11/2014

PRODUCT DESCRIPTION

- A solvent-based wax used to enhance various Dekster finishes. When applied and polished it accentuates and lifts the finish it is being applied to.

COLOUR RANGE

- Clear, metallic and brown

PACKAGING

- 1.7KG / 500gsm

RECOMMENDED FOR

- INTERIOR surfaces
- Used as a finishing coat over Dekster 121 colour retaining primer and chalk paint

NOT RECOMMENDED FOR

- Not suitable for exterior use, or as a sealer. Do not apply near sources of heat eg. fireplaces, as it can become soft and dirt retentive when exposed to heat

APPLICATION

- Please note : For more information on surface preparation refer to the application procedure on the data sheet of your chosen Dekster finish (available on request from Dekster stores)
- Apply the first coat of Dekster Wall Wax to chosen surface with a lint-free mutton cloth. Immediately after completing the entire wall, polish by hand or by Orbital buffing machine.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 411 WALL/FURNITURE WAX

(Page 2 of 4)

V1-28/11/2014

- Allow to dry for 30 minutes and apply a second coat of Dekster Wall Wax in the same manner.
- The more coats of Dekster Wall Wax applied, the more lustrous and rich the coating will be.
- Important: Earthcote Pandomo and Stucco must be sanded with 320 grit water paper before applying Dekster 121 colour retaining primer and waxing. Earthcote Worn Leather Paint does not require sanding before applying Wall Wax.

HEALTH AND SAFETY

- Please read instructions on container
- Avoid skin contact, do not inhale vapours
- Skin : wash well with soap and water
- Eyes: Flush with water & immediately seek medical attention
- Read 16 point Safety Data Sheet

SPREAD RATE

- +/- 40 m² per 1.7kg tin
- Note: The spread rates quoted are approximate and should only be used as a guide as the actual rate will vary depending on the condition and porosity of the substrate.

OVERCOATING TIMES

- 30 minutes
- Note : It is very important that over coating times, as set out for the various products, are adhered to and also that the prevailing weather conditions are taken into account. Ambient and substrate temperatures, humidity and wind etc, can influence drying times of all coatings. Performance problems can occur if any of the previous coats have not been allowed to dry properly before being over coated.
- Important : To prevent surface contamination, coatings must not be left longer than 48 hours between coats. If environmental or weather conditions have caused surface contamination, all surfaces must be thoroughly washed down before applying the next coating.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 411 WALL/FURNITURE WAX

(Page 3 of 4)

V1-28/11/2014

CLEANERS/SOLVENTS

- Mineral Turpentine

PREVENTING PROBLEMS AND GENERAL INFORMATION

- Dekster Wall Wax is purely a decorative finish and offers limited sealing properties.
- For splash backs or wet areas, and surfaces behind hobs or stoves, apply 1 or 2 coats of Colour Retaining Primer followed by 2 coats of Wall Wax.
- Do not apply too thickly in first application.
- Avoid down tools during the application process to prevent lap marks and variances in colour or texture. Work from corner to corner, or from a natural cut off point to another. Do not attempt touch ups, but redo complete panels. Store in dry ambient conditions. Shelf life 12 months

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 411 WALL/FURNITURE WAX

(Page 4 of 4)

V1-28/11/2014

TECHNICAL DATA

VISCOSITY	: N/A
SPECIFIC GRAVITY	: 0.852 G/ML +/- 0,010
PH	: NA
WEIGHT SOLIDS CONTENT	: 21% (+/- 2%)
FINENESS OF GRIND	: N/A
VOLUME SOLIDS CONTENT	: NOT DETERMINED
PIGMENT VOLUME CONCENTRATION	: NOT DETERMINED
SPREAD RATE	: 40M ² /LITRE PER 1.7KG TIN
DRY FILM THICKNESS	: NA
SURFACE DRY	: NA
HARD DRY	: NA
OVERCOAT	: >30 MINUTES
SHEEN 20°	: NA
SHEEN 60°	: NA
SHEEN 85°	: NA
DILUANT/CLEANING	: MINERAL TURPENTINE
APPLICATION TEMPERATURES	: > 10° <35°
STORAGE TEMPERATURES	: > 5° <35°
SHELF LIFE IN UNOPENED CONTAINERS	: 12 MONTHS
DRYING MECHANISM	: NA
SCRUBS	: NA
VEHICLE TYPE	: NOT DETERMINED
PIGMENT TYPE	: NA
APPLICATION	: LINT FREE MUTTON CLOTH

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140