

# Dekster

Head Office  
24 Fabriek Street, Kuils River, 7580  
P.O.Box 131, Kuils River, 7579  
South Africa

Tel: +27 (0)21 903 6042  
Fax: +27 (0)86 611 0405  
<http://www.dekster.co.za>  
E-mail : [info@dekster.co.za](mailto:info@dekster.co.za)

## DATA SHEET

### DEKSTER 502 WATER BASED ETCH PRIMER

(Page 1 of 3)

VI-28/11/2014

#### DESCRIPTION

- Dekster 502 Water Based Etch Primer is an anti-corrosive primer for steel containing rust inhibitors.

#### PROPERTIES

- Non-toxic and non-irritating
- Lead and chromate free
- Quick drying and time saving
- Prevents rust and rust creep
- Non-flammable
- Easy application by brush or spray
- Easy cleaning of equipment with water

#### USES

- Anti-corrosion primer for steel
- Suitable for enclosed spaces
- No discomfort from odours or fumes
- Can be over-coated with most paints including Epoxy, Polyurethane, Vinyl and Alkyd Enamel top coats

#### SURFACE PREPARATION

- New Steel: Blast-clean to Sa 2 ½. (ISO 850 1-1:1988/SS 05 5900)
- Galvanised Steel: Clean with Galv-O-Clean to a water break free surface
- Aged, Rusty Steel: Mechanically clean to St 2 (Remove all loose rust, old paint, oil and dirt)

Note: In coastal areas or where there is industrial fallout use HOLDTIGHT®102 diluted 50:1 with fresh water to remove soluble salts to avoid osmotic blistering and resultant coating failure.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

# Dekster

Head Office  
24 Fabriek Street, Kuils River, 7580  
P.O.Box 131, Kuils River, 7579  
South Africa

Tel: +27 (0)21 903 6042  
Fax: +27 (0)86 611 0405  
<http://www.dekster.co.za>  
E-mail : [info@dekster.co.za](mailto:info@dekster.co.za)

## DATA SHEET

### DEKSTER 502 WATER BASED ETCH PRIMER

(Page 2 of 3)

V1-28/11/2014

#### APPLICATION

- The product is supplied ready for use with no thinning required. If sprayed, water may be added to achieve the required viscosity. Apply 2 thin coats to achieve uniform coverage rather than 1 thick coat.

#### SAFETY

- Although Dekster 502 is water based and relatively safe to use it is recommended that the 16 point Material Safety Data Sheet is referred to.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

# Dekster

Head Office  
24 Fabriek Street, Kuils River, 7580  
P.O.Box 131, Kuils River, 7579  
South Africa

Tel: +27 (0)21 903 6042  
Fax: +27 (0)86 611 0405  
<http://www.dekster.co.za>  
E-mail : [info@dekster.co.za](mailto:info@dekster.co.za)

## DATA SHEET

### DEKSTER 502 WATER BASED ETCH PRIMER

(Page 3 of 3)

VI-28/11/2014

#### TECHNICAL DATA

<b>TYPE</b>	Acrylic Emulsion
<b>NUMBER OF COMPONENTS</b>	One
<b>COLOUR</b>	Black, Red Oxide
<b>VOLUME SOLIDS</b>	45-47%
<b>DENSITY</b>	1,37 gm/cm <sup>2</sup>
<b>CONSISTENCY</b>	Liquid
<b>FINISH</b>	Matt
<b>AVERAGE SPREAD RATE</b>	10 m <sup>2</sup> /ℓ/coat
<b>OVERCOATING TIME (Min)</b>	1-2hrs
<b>COATING SYSTEM (Max)</b>	Unlimited
<b>TOUCH DRY</b>	½ - 2 Hrs
<b>WET FILM THICKNESS</b>	100 µm
<b>DRY FILM THICKNESS</b>	45 µm
<b>THINNER</b>	Water
<b>FLASH POINT</b>	Not Applicable
<b>PACK SIZE</b>	1 litre and 5 litre
<b>SHELF LIFE</b>	12 months

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140