

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 513 FOOD GRADE EPOXY LINING

(Page 1 of 3)

VI-22/11/2013

DESCRIPTION

- Dekster 513 is a solvent free, high build epoxy coating utilizing resins compliant with the requirements of FDA regulation 21CFR 175.300 for coatings or tank linings in contact with food, edible oils, water or alcoholic beverages containing up to 12% alcohol by volume.

PROPERTIES

- Potable water tank linings
- Brewery and wine tank linings
- Lining of steel and concrete tanks & silos

CHEMICAL RESISTANCE

- Resist most common aggressive chemicals, petroleum products, dilute acids and alkalis, aliphatic solvents and sea water, wine and beer.

INSTRUCTIONS

- **PREPARATION:** Grit-blast to Sa 2½ (ISO 8501-1:1988). If soluble salt levels are above 30mg/m², high pressure wash with Holdtight 102 diluted 50:1 with clean water.
- **PRIMING:** Steel: Dekster 501. Concrete or Plaster : Dekster101
- **MIXING:** Mix the epoxy and activator in the proportions given using a mechanical mixer. Make sure only sufficient quantity is mixed that can be used within 60 minutes.
- **APPLICATION:** Apply 2 or 3 coats by brush, roller or airless spray to achieve minimum 500µ DFT. Subsequent coats should be applied as soon as possible after each coat is sufficiently hard enough to walk on. (Maximum over-coating time 24hrs @ 25°C) May also be used with fibreglass reinforcing.
- **CLEANING EQUIPMENT:** Clean equipment immediately after use with Dekster Water Soluble Brush Cleaner.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 513 FOOD GRADE EPOXY LINING

(Page 2 of 3)

VI-22/11/2013

TOXICITY

- Although Dekster 513 is relatively non-toxic, it is recommended that the normal precautions in dealing with conventional Epoxy systems are adhered to. Refer to the 16 point Material Safety Data Sheet.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 513 FOOD GRADE EPOXY LINING

(Page 3 of 3)

VI-22/11/2013

TECHNICAL DATA

COLOUR	: White, grey or green
MIXING RATIO (By Volume)	: 2 : 1
POT LIFE (500ml @ 25°C)	: 90 Min
TOUCH DRY @ 25°C	: 8-10 Hrs
PRACTICAL CURE	: 24 Hrs
FULL CURE	: 7 Days
AVERAGE SPREAD RATE	: 2 coats @4m ² /l/coat
DFT per coat	: 2 x 250µ
OVERCOATING TIME	: 10-36 hours
APPLICATION TEMPERATURE	: 10-35°C
SERVICE TEMPERATURE	: Wet 50°C Dry 70°C
VOLUME SOLIDS	: 100%
PACKAGING	: 3, 15 and 60 litres
SHELF LIFE	: 12 months

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140