

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 717 SUPER RUST CONVERTER

(Page 1 of 3)

V1-28/11/2014

DESCRIPTION

- A ready to use water based rust converter and protective coating in one product.

USES

- Where blast cleaning is impractical

PROPERTIES

- Converts iron oxide (rust) to ferrous tannate
- Colour changes to black when reaction is complete
- Easy to apply by brush, roller or spray
- Water based, VOC compliant and environmentally friendly.

PREPARATION AND APPLICATION

- All surfaces to be clean and sound and free of dust, oil and dirt
- Wire brush to remove loose rust
- Apply 1 or 2 coats by brush, roller or spray @ 10 – 12m²/litre per coat
- Clean all equipment with water

OVERCOATING

- Allow to dry for 3-4hrs then overcoat with water based or solvent based top coats.
- Different surfaces and environmental conditions require specific painting systems to produce the best possible results. It is therefore recommended that you contact a Dekster Sales Representative for advice on all your painting requirements, whenever possible.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 717 **SUPER RUST CONVERTER**

(Page 2 of 3)

V1-28/11/2014

HEALTH AND SAFETY

- Wear suitable face masks when spraying. Wash up with soap and water. Refer to the 16 point Material Safety data Sheet.

HOW TO SPECIFY

- All Rusted surfaces to be suitable prepared and then coated with Dekster 512 Super Rust Converter according to the manufacturer's instructions

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140

Dekster

Head Office
24 Fabriek Street, Kuils River, 7580
P.O.Box 131, Kuils River, 7579
South Africa

Tel: +27 (0)21 903 6042
Fax: +27 (0)86 611 0405
<http://www.dekster.co.za>
E-mail : info@dekster.co.za

DATA SHEET

DEKSTER 717 SUPER RUST CONVERTER

(Page 3 of 3)

VI-28/11/2014

TECHNICAL DATA

TYPE	: A tannate based rust converter
COLOUR	: Milky yellow which changes to black
DRYING TIME	Temperature 5°C 10°C 20C 30°C Surface Dry 2Hrs 1Hr ½Hr ½Hr Hard Dry 9Hrs 8Hrs 6Hrs 4Hrs
No. OF COATS	: 1 or 2
RECOAT TIME	: 3 to 48hrs
APPEARANCE	: Matt black when cured
VOLUME SOLIDS	: 40%
SPREAD RATE	: 10- 12m ² /litre
APPLICATION TEMP.	: 5 to 45°C
PACKAGING	: 0.5L , 1L, 5L, 25L
CLEANING	: Water

The technical data furnished is obtained from controlled laboratory tests under ideal application conditions. No guarantee of any performance characteristic is therefore given or implied and we do not hold ourselves responsible for any consequential damage of whatsoever nature that may arise from use of our products. In the event of a proven fault our liability will be limited to the replacement of the product only. It is the users' responsibility to confirm the currency of product data sheets.

DEKSTER COATINGS (PTY) LTD REG NO. 2013/106812/07

Vat reg no:4120240140